

Thermobel Top:

① 6 mm Planibel Clearlite Annealed ② 16 mm Argon 90% ③ 4 mm iplus 1.1 pos.3 Annealed

Performance data

☀ Light properties - EN 410

Light transmission : τ_v [%]	81
External light reflection : ρ_v [%]	12
Internal light reflection : ρ_{vi} [%]	12
Colour rendering index : Ra [%]	98

🔥 Energy properties - EN 410

Solar factor : g [%]	63
External energy reflection : ρ_e [%]	26
Internal energy reflection : ρ_{ei} [%]	27
Direct energy transmission : τ_e [%]	57
Energy absorption glass 1 : α_{e1} [%]	10
Energy absorption glass 2 : α_{e2} [%]	7
Total energy absorption : α_e [%]	17
Shading coefficient : SC	0.72
UV transmission : τ_{uv} [%]	42
Selectivity	1.28

🌡 Thermal properties - EN 673

Thermal transmittance (vertical) : U_g [W/(m ² .K)]	1.1
Thermal transmittance (Roof, horizontal) : U_g [W/(m ² .K)]	1.7

☀ Summer solar factor - RT 2012

Sg1 : Sg1 [%]	57
Sg2 : Sg2 [%]	6
Sg3 : Sg3 [%]	0

☀ Winter solar factor - RT 2012

Sg1 : Sg1 [%]	57
Sg2 : Sg2 [%]	6
Sg3 : Sg3 [%]	0

🔊 Acoustic properties

Direct airborne sound insulation - ESTIMATED : R_w (C;Ctr) [dB] ¹	36 (-1;-5)
--	------------

🛡 Safety properties

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	NPD
Bullet resistance - EN 1063	NPD
Burglar resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	NPD / NPD
Explosion resistance - EN 13541	NPD

📏 Thickness and weight

Nominal thickness : [mm]	26.0
Weight : [kg/m ²]	25

¹ The sound reduction indexes are estimated and neither tested, nor calculated. They correspond to glazing with dimensions 1230 mm by 1480 mm according to EN ISO 10140-3. In-situ performances may vary according to the effective glazing dimensions, supporting system, installation, environment, noise sources etc. The accuracy of the given indexes is +/- 2 dB.