

① Stratobel Clearlite 55.2 Annealed

Performance data

☀️ Light properties - EN 410

| | |
|---|-----------|
| Light transmission : τ_v [%] | 88 |
| External light reflection : ρ_v [%] | 8 |
| Internal light reflection : ρ_{vi} [%] | 8 |
| Colour rendering index : Ra [%] | 98 |

🔥 Energy properties - EN 410

| | |
|---|-------------|
| Solar factor : g [%] | 78 |
| External energy reflection : ρ_e [%] | 7 |
| Internal energy reflection : ρ_{ei} [%] | 7 |
| Direct energy transmission : τ_e [%] | 74 |
| Energy absorption glass 1 : α_{e1} [%] | 19 |
| Total energy absorption : α_e [%] | 19 |
| Shading coefficient : SC | 0.90 |
| UV transmission : τ_{uv} [%] | 0 |
| Selectivity | 1.12 |

🌡️ Thermal properties - EN 673

| | |
|--|------------|
| Thermal transmittance (vertical) : U_g [W/(m ² .K)] | 5.5 |
| Thermal transmittance (Roof, horizontal) : U_g [W/(m ² .K)] | 5.5 |

☀️ Summer solar factor - RT 2012

| | |
|---------------|-----------|
| Sg1 : Sg1 [%] | 74 |
| Sg2 : Sg2 [%] | 7 |
| Sg3 : Sg3 [%] | 0 |

☀️ Winter solar factor - RT 2012

| | |
|---------------|-----------|
| Sg1 : Sg1 [%] | 74 |
| Sg2 : Sg2 [%] | 5 |
| Sg3 : Sg3 [%] | 0 |

🔊 Acoustic properties

| | |
|--|-------------------|
| Direct airborne sound insulation - ESTIMATED : R_w (C;Ctr) [dB] ¹ | 35 (-1;-3) |
|--|-------------------|

🛡️ Safety properties

| | |
|--|------------|
| Resistance to fire - EN 13501-2 | NPD |
| Reaction to fire - EN 13501-1 | A1 |
| Bullet resistance - EN 1063 | NPD |
| Burglar resistance - EN 356 | P2A |
| Pendulum body impact resistance - EN 12600 | 1B1 |
| Explosion resistance - EN 13541 | NPD |

📏 Thickness and weight

| | |
|-------------------------------|-------------|
| Nominal thickness : [mm] | 11.0 |
| Weight : [kg/m ²] | 28 |

¹ The sound reduction indexes are estimated and neither tested, nor calculated. They correspond to glazing with dimensions 1230 mm by 1480 mm according to EN ISO 10140-3. In-situ performances may vary according to the effective glazing dimensions, supporting system, installation, environment, noise sources etc. The accuracy of the given indexes is +/- 2 dB.